



STEEL FINISHES--Misc. Interior Steel

A. Surface Preparation: Clean surfaces according to SSPC-SP 5/ NACE No. 1, "White Metal Blast Cleaning."

1. Powder Coating: After cleaning, apply a polyester epoxy blend or polyester coat total dry film thickness of not less than 4 mils (0.10 mm). Comply with coating manufacturer's written instructions.

**Bosco Powder Coating  
A&P MetalWerx & Design**

137 Sugar Ave, Billings, MT 59101

phone: (406) 652-7147 fax: (406) 652-7145

[info@boscopowdercoating.com](mailto:info@boscopowdercoating.com)